

MATERIAL SPECS

	Material	General Description	Hardness (Shore A)	Tensile Strength MNm-2	Elongation (%)	Operating Temperature		Electrical Insulation
						Low °C	High °C	
Dip Moulded Vinyl	9238	General Purpose Glossy	75	15	300	-30	100	Good
	HT-201	Hi -Temp Resistant	80	16	250	-18	230	Good
	9400M	Medical Grade	62	13	350	-20	60	~
	9400	Softer Standard Grade	62	13	350	-20	60	~
	9240M	Medical Grade Glossy, Harder	80	16	275	N/A	60	Good
	9240	General Purpose Glossy, Harder	85	16	275	20	60	Good
	9220	Anti-Static	70	14	300	-29	121	Good
	9100	Textured	60	12	350	-29	66	~
Rubber	Silicone	Extra Temperature (EHTSi)	~	6	300	-76	316	~
	EPDM	Hi-Temp Chemical Resistant	~	10	320	-55	246	~
Resins	LDPE	Low Density Polyethylene	~	600-2300 PSI	~	-70	79	~
	HDPE	High Density Polyethylene	~	3100-5500 PSI	~	-18	102	~
	PP	Polypropylene	~	4300-5500 PSI	~	-70	121	~
	TPE	Thermoplastic Elastomer	82	580-1610 PSI	~	-60	135	~

Additional Formulas, Compounds & Resins Available, Please Contact Sales.

Material Maximum Temperature Specifications

Temperatures shown are guidelines. Please request a **FREE** sample for your testing.

60° C	100° C	102° C	121° C	135° C	246° C	316° C
9240	9100	9238	9220	TPE	HT201	SILICONE
9400	LDPE	HDPE	PP		EPDM	

COLOUR OPTIONS

9238 Formula Vinyl:



MINI-PAKS

If you require smaller quantities, **MOCAP** offers the convenience of Mini-Paks. All Polyethylene Parts and most common sizes of Vinyl Caps are available in these smaller quantities. **MOCAP** Silicone and EPDM Rubber Masking Products are also available in Mini-Pak quantities. Please contact **MOCAP** Sales or Customer Service for details.

TERMS & CONDITIONS OF SALE

Minimum Order: £60/90€ - £30/45€ for MINI-PAKS

Terms: Net 30 Days from shipment, subject to credit approval. Otherwise Pro forma Invoice.
Most Major Credit / Debit Cards are accepted.



Returns: All returns must be authorised by **MOCAP**. Unauthorised returns cannot be accepted. Production run parts are not returnable, unless defective. Stock parts subject to £30.00 restocking charge. All claims for returns must be made within 30 days from invoice date.

Over/Under Runs: Due to the difficulty in producing exact quantities, all orders within 10% of quantity ordered must be considered complete.

Samples: **MOCAP** recommends approval of samples before ordering, especially on production run parts. Application Advisor is offered as a guideline. Please request **FREE** Samples to test within your application. Returns will not be accepted if samples were refused or not requested.

For a complete list of terms and conditions visit our web site at: www.mocap.co.uk